



3475 Direct to Metal Remanufactured Flat Latex Finish

CHARACTERISTICS:

- Remanufactured
- Contains a minimum of 50% post-consumer paint
- Environmentally Preferred
- Excellent Adhesion
- Weather Resistant
- Durable
- Easy Application
- Soap & Water Clean-Up
- Low Odor

PHYSICAL PROPERTIES:

- Finish: Flat
- Sheen @ 60° ----- 2-6%

VOLUME SOLIDS:

- Approximately 35-45%

VISCOSITY:

Package Viscosity 85-95 KU

PERFORMANCE PROPERTIES:

Approximately 300-400 sq. ft. per gallon @ 1.5 mils depending on substrate and application method, porosity and surface texture.

Approximate coverage for each coat.

Recommended Dry Film Thickness:

- 3-6 Mils DFT

MILDEW RESISTANT:

This coating contains agents that inhibit the growth of mildew on the surface of this coating.

DRYING TIME:

To Touch ----- 30-60 minutes

To Re-coat ----- 2 hours

Lower temperatures, humidity, thicker film or improper ventilation will increase these times.

SUBSTRATES:

ALUMINUM, GALVANIZED STEEL:

Made for application on properly prepared non-ferrous metal substrates. Apply finish to primed or previously painted metal with no visible rust. Clean the surface to remove any dirt, efflorescence, grease, oil, wax, mildew or other foreign material.

FERROUS METAL:

Made for application on properly prepared ferrous metal substrates. Recommend rust inhibitive primer prior to finish coat.

PREVIOUSLY PAINTED SURFACES:

Patch all voids with the appropriate patching or caulking material. Wash, rinse, scrape, sand and clean the surface to remove any chalk, dirt, grease, oil, wax, mildew, loose paint or other foreign material.

APPLICATION:

Product may be applied with brush, roller or airless sprayer. Maintain a "wet edge" and apply coating uniformly. Prevent flash rusting by priming all bare metal surfaces same day or immediately following cleaning application.

THINNING:

Product intended for use at package consistency. If thinning is desired, do not thin more than 1/2 pint per gallon.

CLEAN-UP:

Clean up equipment and area immediately with soapy water.

Application:

Do not apply where material, air or surface temperature is below 50° F. Surfaces and ambient temperatures must be between 48° F and 100° F, 5° above dew point and remain above 48° F for a minimum of four hours after application. All paint products should be tested for adhesion, appearance, color and compatibility prior to application.

PERSONAL:

Paint may be irritating to eyes, nose and skin. Avoid contact with eyes. In case of eye contact, flush at least fifteen minutes and call a physician immediately.

STORAGE:

KEEP FROM FREEZING STORE ABOVE 50° F

MAXIMUM VOC:

<200 GRAMS PER LITER

<1.25 POUNDS PER GALLON

CAUTION:

Avoid contact with eyes, skin and clothing.

Do not take internally.

Wash thoroughly after handling.

Close container after each use.

For additional safety information consult the Material Safety Data Sheet (MSDS)

KEEP OUT OF REACH OF CHILDREN.

USE ONLY WITH ADEQUATE VENTILATION.

© Copyright VRI, Inc. 2013 All rights reserved Internationally

Visions Recycling, Inc. 4105 South Market Court • Suite A, Sacramento, CA 95834

Toll Free: 800-770-7664 / Phone: 916-564-9121 / Fax: 916-568-1485

www.visionsrecycling.com

VRI 100 PDS Revision: 08-21-2014